



Bulgaria, 5300 Gabrovo, 1 "Uspeh" Str., office 3;  
phone/fax: +359 66 80 50 11; mob:+359 888 693 123  
e-mail: tempus\_link@abv.bg

---

OCTOL, HMX/TNT

*Octolite, oktol*

*Class 1.1D, UN 0226*

*Transport RID/ADR, IMDG*

*Technical specification*

90/10	
1. Color and appearance	Yellowish granules; without mechanical impurities
2. HMX content, % (m/m)	90±2,0
3. TNT content, % (m/m)	10,0±2,0
4. Moisture and volatile matters, % (m/m), max	0,10
5. Acidity (as CH <sub>3</sub> , COOH), % (m/m), max	0,02
6. Insoluble in benzene or acetone, % (m/m), max	750
7. Viscosity HMX/TNT 60/40, in 85 °C, ø 8mm, CST	informative
8. Granulation:, (m/m) in % (m/m), passes through sieve, mm	
2,300	100
0,150	Max 12