



Bulgaria, 5300 Gabrovo, 1 "Uspeh" Str., office 3;
phone/fax: +359 66 80 50 11; mob:+359 888 693 123
e-mail: tempus_link@abv.bg

PENTOKS, PETN/TNT/KCIO₄
Class 1.1D

Technical specification

	Grade I	Grade II
1. Color and appearance	Brown granules, without mechanical impurities	
2. TNT content, % (m/m)	9,0±2,0	7,0±1,7
3. KClO ₄ content, % (m/m)	10,0±2,0	30,0±2,0
4. Moisture and volatile matters, % (m/m), max	0,10	
5. Bulk density, g/dm ³ , min	700	
6. Granulation (m/m) in % (m/m), passes through sieves, mm		
1,700	100	
0,150	max 12	